

WOLF OFFICIALTECH 10W40 ULTRA MS

31/03/2026
65603

This is a full synthetic lubricant based on carefully selected very high quality base oils, which satisfies the highest performance standards for large trucks. It can be used for engines equipped with after treatment systems, in combination with low-sulfur diesel (maximum 50 ppm).

APPLICATIONS

Specifically recommended for large truck engines to satisfy the EURO V-standard and suitable for most Euro VI engines. Perfectly compatible with all after-treatment systems and devices (EGR, SCR, DPF, etc.) in combination with low sulfur diesel (max 50 ppm). Can also be used in older diesel engines (Euro II, III, IV). Also suitable for some gas-powered engines (CNG).

FEATURES

Aftertreatment protection: full aftertreatment systems protection
Total engine protection: outstanding engine cleanliness and durability
Fuel economy: lower fuel consumption and CO2 emissions

SPECIFICATIONS

ACEA	E11	MACK	EO-M PLUS
ACEA	E6-16	MAN	M3271-1
ACEA	E7	MAN	M3477
ACEA	E8	MB	226.9
ACEA	E9-16	MB	228.31
API	approval CI-4	MB	228.51
API	SL	MTU	approval Oil Category 3.1
JASO	DH-1	MTU	Oil Category 2.1
JASO	DH-2	RENAULT	approval RLD-2
ALLISON	C4	RENAULT	RGD
CATERPILLAR	ECF-1a	RENAULT	RLD
CATERPILLAR	TO-2	RENAULT	RXD
CUMMINS	CES 20076	SCANIA	LA
CUMMINS	CES 20077	VOITH	Retarder Oil Class A
CUMMINS	CES 20078	VOLVO	approval VDS-3
DAF	EXTENDED DRAIN	WEICHAH	WP7NG Natural Gas Engine
DETROIT DIESEL	DFS 93K215		
DEUTZ	approval DQC-IV-18 LA		
DEUTZ	DQC IV-10 LA		
DEUTZ	TTCD		
DTFR	13D100		
DTFR	15C100		
DTFR	approval 15C110		
FORD	WSS-M2C171-F1		
IVECO	18-1804 Classe T2 E7		
JD	JDQ-78X		
MACK	approval EO-N		

WOLF OIL CORPORATION NV

G. Gilliotstraat 52 – 2620 Hemiksem – Belgium
Tel. +32 (0)3 870 00 00

www.wolf lubes.com



TYPICAL CHARACTERISTICS

Test	Method	Unit	Average results
Density at 15°C	ASTM D4052	g/ml	0.859
Kinematic viscosity at 40°C	ASTM D445	mm ² /s	87.9
Kinematic viscosity at 100°C	ASTM D445	mm ² /s	13.7
Viscosity index	ASTM D2270		159
B.N. (HClO4 method)	ASTM D2896	mg KOH/g	10.4
Pour point	ASTM D6892	°C	-36
CCS viscosity at -25°C	ASTM D5293	mPa.s	5200
Sulfated Ash	ASTM D874	Mass %	0.99
Flash Point COC	ASTM D92	°C	230

We reserve the right to alter the general characteristics of our products in order to let our customers benefit of the latest technical evolutions.

WOLF OIL CORPORATION NV

G. Gilliotstraat 52 – 2620 Hemiksem – Belgium
Tel. +32 (0)3 870 00 00

www.wolflubes.com

